

Application No. 10/035,736

AMENDMENTS TO THE CLAIMS:


This listing of claims will replace all prior versions, and listings of claims in the application:

LISTING OF CLAIMS:


1. (Currently Amended) An ink composition comprising (a) water, (b) an anionic dye, (c) a polyquaternary amine compound, and (d) a quaternary ammonium substituted UV absorbing compound which is a hydroxybenzophenone quaternary compound.

Application No. 10/035,736

2. (Original) An ink composition according to claim 1 wherein the polyquaternary amine compound is of one of the formulae



or



wherein n is an integer representing the number of repeat monomer units, R_1 and R_7 each, independently of the other, is an alkylene group, an arylene group, an arylalkylene group, or an alkylarylene group, and R_2 , R_3 , R_4 , R_5 , and R_6 each, independently of the others, are hydrogen atoms, alkyl groups, aryl groups, arylalkyl groups, or alkylaryl groups.

3. (Original) An ink composition according to claim 1 wherein the polyquaternary amine compound is selected from the group consisting of polydiallyl ammonium compounds, polyquaternized polyvinylamines, polyquaternized polyallyl amines, epichlorohydrin/amine copolymers, cationic amido amine copolymers, copolymers of vinyl pyrrolidone and a vinyl imidazolium salt, and mixtures thereof.

Application No. 10/035,736

4. (Original) An ink composition according to claim 1 wherein the polyquaternary amine compound is a polydiallyl dimethyl ammonium compound.

5. (Original) An ink composition according to claim 1 wherein the polyquaternary amine compound is present in the ink in an amount of at least about 0.01 percent by weight of the ink and wherein the cationic polymer is present in the ink in an amount of no more than about 50 percent by weight of the ink.

6. (Cancelled)

7. (Cancelled)

8. (Cancelled)


9. (Original) An ink composition according to claim 1 wherein the quaternary ammonium substituted UV absorbing compound is present in the ink in an amount of at least about 0.05 percent by weight of the ink, and wherein the quaternary ammonium substituted UV absorbing compound is present in the ink in an amount of no more than about 10 percent by weight.

10. (Original) An ink composition according to claim 1 wherein the ink further contains a nonpolymeric salt.


Application No. 10/035,736

11. (Currently Amended) An ink composition comprising (a) water, (b) a complex of (i) an anionic dye and (ii) a polyquaternary amine compound, and (c) a quaternary ammonium substituted UV absorbing compound which is a hydroxybenzophenone quaternary compound.

12. (Original) An ink composition according to claim 11 wherein the polyquaternary amine compound is of one of the formulae



or



wherein n is an integer representing the number of repeat monomer units, R₁ and R₇ each, independently of the other, is an alkylene group, an arylene group, an arylalkylene group, or an alkylarylene group, and R₂, R₃, R₄, R₅, and R₆ each, independently of the others, are hydrogen atoms, alkyl groups, aryl groups, arylalkyl groups, or alkylaryl groups.

Application No. 10/035,736

13. (Original) An ink composition according to claim 11 wherein the polyquaternary amine compound is selected from the group consisting of polydiallyl ammonium compounds, polyquaternized polyvinylamines, polyquaternized polyallylamines, epichlorohydrin/amine copolymers, cationic amido amine copolymers, copolymers of vinyl pyrrolidinone and a vinyl imidazolium salt, and mixtures thereof.

14. (Original) An ink composition according to claim 11 wherein the polyquaternary amine compound is a polydiallyl dimethyl ammonium compound.

15. (Original) An ink composition according to claim 11 wherein the polyquaternary amine compound is present in the ink in an amount of at least about 0.01 percent by weight of the ink and wherein the cationic polymer is present in the ink in an amount of no more than about 50 percent by weight of the ink.

16. (Cancelled)

17. (Cancelled)

18. (Cancelled)

Application No. 10/035,736

19. (Original) An ink composition according to claim 11 wherein the quaternary ammonium substituted UV absorbing compound is present in the ink in an amount of at least about 0.05 percent by weight of the ink, and wherein the quaternary ammonium substituted UV absorbing compound is present in the ink in an amount of no more than about 10 percent by weight.

20. (Original) An ink composition according to claim 11 wherein the ink further contains a nonpolymeric salt.

21. (Currently Amended) A process which comprises incorporating into an ink jet printing apparatus an ink composition comprising (a) water, (b) an anionic dye, (c) a polyquaternary amine compound, and (d) a quaternary ammonium substituted UV absorbing compound which is a hydroxybenzophenone quaternary compound, and causing droplets of the inks to be ejected in an imagewise pattern onto a recording substrate.

22. (Original) A process according to claim 21 wherein the printing apparatus employs a thermal ink jet process wherein the ink in the nozzles is selectively heated in an imagewise pattern, thereby causing droplets of the ink to be ejected in imagewise pattern.

Application No. 10/035,736

23. (Original) A process according to claim 21 wherein the printing apparatus employs a piezoelectric ink jet process wherein droplets of the ink are caused to be ejected in imagewise pattern by oscillations of piezoelectric vibrating elements.

24. (Currently Amended) A process which comprises incorporating into an ink jet printing apparatus an ink composition comprising (a) water, (b) a complex of (i) an anionic dye and (ii) a polyquaternary amine compound, and (c) a quaternary ammonium substituted UV absorbing compound which is a hydroxybenzophenone quaternary compound, and causing droplets of the inks to be ejected in an imagewise pattern onto a recording substrate.

25. (Original) A process according to claim 24 wherein the printing apparatus employs a thermal ink jet process wherein the ink in the nozzles is selectively heated in an imagewise pattern, thereby causing droplets of the ink to be ejected in imagewise pattern.

26. (Original) A process according to claim 24 wherein the printing apparatus employs a piezoelectric ink jet process wherein droplets of the ink are caused to be ejected in imagewise pattern by oscillations of piezoelectric vibrating elements.

27. (Cancelled)


28. (Cancelled)

Application No. 10/035,736

29. (Cancelled)

30. (Cancelled)


31. (Currently Amended) An ink composition ~~according to claim 1 comprising (a) water, (b) an anionic dye, (c) a polyquaternary amine compound, and (d) a quaternary ammonium substituted UV absorbing compound,~~ wherein the quaternary ammonium substituted UV absorbing compound is of the general formula



wherein R₁ is an alkylene group, an arylalkylene group, or a polyalkyleneoxy group, and R₂, R₃, and R₄ each, independently of the others, is a hydrogen atom, an alkyl group, an aryl group, an arylalkyl group, an alkylaryl group, an alkoxy group, or a polyalkyleneoxy group.

Application No. 10/035,736


32. (Currently Amended) An ink composition ~~according to claim 1 comprising (a) water, (b) an anionic dye, (c) a polyquaternary amine compound, and (d) a quaternary ammonium substituted UV absorbing compound,~~ wherein the quaternary ammonium substituted UV absorbing compound is of the general formula



wherein R₁ is an alkylene group, an arylalkylene group, or a polyalkyleneoxy group, and R₂, R₃, and R₄ each, independently of the others, is a hydrogen atom, an alkyl group, an aryl group, an arylalkyl group, an alkylaryl group, an alkoxy group, or a polyalkyleneoxy group.

Application No. 10/035,736




33. (Currently Amended) An ink composition according to claim 1 comprising (a) water, (b) an anionic dye, (c) a polyquaternary amine compound, and (d) a quaternary ammonium substituted UV absorbing compound, wherein the quaternary ammonium substituted UV absorbing compound is of the general formula



wherein R₁ is an alkylene group, an arylalkylene group, or a polyalkyleneoxy group, and R₂, R₃, and R₄ each, independently of the others, is a hydrogen atom, an alkyl group, an aryl group, an arylalkyl group, an alkylaryl group, an alkoxy group, or a polyalkyleneoxy group.


Application No. 10/035,736

34. (Previously Presented) An ink composition according to claim 1 wherein the quaternary ammonium substituted UV absorbing compound is of one of the general formulae



or

Application No. 10/035,736



wherein R_1 is an alkylene group, an arylalkylene group, or a polyalkyleneoxy group, and R_2 , R_3 , and R_4 each, independently of the others, is a hydrogen atom, an alkyl group, an aryl group, an arylalkyl group, an alkylaryl group, an alkoxy group, or a polyalkyleneoxy group.

Application No. 10/035,736

35. (Cancelled)

36. (Cancelled)


37. (Cancelled)

38. (Cancelled)

39. (Cancelled)

Application No. 10/035,736


40. (Currently Amended) An ink composition according to claim 11 comprising (a) water, (b) a complex of (i) an anionic dye and (ii) a polyquaternary amine compound, and (c) a quaternary ammonium substituted UV absorbing compound, wherein the quaternary ammonium substituted UV absorbing compound is of the general formula



wherein R₁ is an alkylene group, an arylalkylene group, or a polyalkyleneoxy group, and R₂, R₃, and R₄ each, independently of the others, is a hydrogen atom, an alkyl group, an aryl group, an arylalkyl group, an alkylaryl group, an alkoxy group, or a polyalkyleneoxy group.

Application No. 10/035,736


41. (Currently Amended) An ink composition ~~according to claim 11 comprising (a) water, (b) a complex of (i) an anionic dye and (ii) a polyquaternary amine compound, and (c) a quaternary ammonium substituted UV absorbing compound,~~ wherein the quaternary ammonium substituted UV absorbing compound is of the general formula



wherein R₁ is an alkylene group, an arylalkylene group, or a polyalkyleneoxy group, and R₂, R₃, and R₄ each, independently of the others, is a hydrogen atom, an alkyl group, an aryl group, an arylalkyl group, an alkylaryl group, an alkoxy group, or a polyalkyleneoxy group.

Application No. 10/035,736




42. (Currently Amended) An ink composition ~~according to claim 11 comprising (a) water, (b) a complex of (i) an anionic dye and (ii) a polyquaternary amine compound, and (c) a quaternary ammonium substituted UV absorbing compound, wherein~~ the quaternary ammonium substituted UV absorbing compound is of the general formula



wherein, R₁ is an alkylene group, an arylalkylene group, or a polyalkyleneoxy group, and R₂, R₃, and R₄ each, independently of the others, is a hydrogen atom, an alkyl group, an aryl group, an arylalkyl group, an alkylaryl group, an alkoxy group, or a polyalkyleneoxy group.


Application No. 10/035,736

43. (Previously Presented) An ink composition according to claim 11 wherein the quaternary ammonium substituted UV absorbing compound is of one of the general formulae



or

Application No. 10/035,736



wherein R₁ is an alkylene group, an arylalkylene group, or a polyalkyleneoxy group, and R₂, R₃, and R₄ each, independently of the others, is a hydrogen atom, an alkyl group, an aryl group, an arylalkyl group, an alkylaryl group, an alkoxy group, or a polyalkyleneoxy group.

44. (Cancelled)